



FLOCHEM INDUSTRIES s.r.l

Mihail Cioranu, 4, sector 5, Bucuresti

Tel./Fax : (+40) 021 410 7809

(+40) 021 410 3026

Mobil : (+40) 0744 567 466

(+40) 0744 425 079

flochem@floerger.ro; www.floerger.ro

SPECIFICATIE TEHNICA

ACTICARBONE 25 KP **CARBUNE ACTIV PUDRA**

August 2008 rev. 4

° **COMPOZITIE**

Carbune activ activat cu abur.

° **DOMENII DE UTILIZARE**

Tratare apa potabila.

Declorinare

° **SPECIFICATII TEHNICE**

METODA	CONTROL	VALORI	UNITATE DE MASURA
AWWA B 600-78	INDICE DE IOD	700 min.	mg/g
CEFIC-86	INDICE METHILENE BLUE	9 min.	ml/0.1g
ASTM D 2867-70	UMIDITATE (IN TIMPUL AMBALARII)	6 max.	%
ASTM D 2866-70	CENUSA	10 max.	%
ASTM D 2862-67	GRANULOMETRIE >100µm	10 max.	%

° **CARACTERISTICE TEHNICE SPECIFICE**

(Bazate pe valorile medii analizate de-a lungul a 2 ani de productie a produsului)

TEST METHOD	CARACTERISTICI	VALORI	UNITATI DE MASURA
AWWA B 600-78	INDICE DE IOD	750	mg/g
CEFIC-86	INDICE METHILENE BLUE	10	ml/0.1g
ASTM D 2867-70	UMIDITATE (IN TIMPUL AMBALARII)	4	%
ASTM D 2866-70	CENUSA	9	%
	DENSITATE	450 ± 50	kg/m ³

° **AMBALARE**

Saci de hartie multistrat a 20 kg net, big bags a 400 kg net, vrac sau alte dimensiuni la solicitarea clientilor. Carbunele activ poate fi stocat mai mult de 2 ani in ambalajul original, in conditii de umiditate scazuta si departe de substante volatile. Esantioane din fiecare lot sunt pastrate timp de 12 luni de la data productiei.